



## Drako HR 240 C

Çelik Halatlar &gt; Yüksek Mukavemetli Çelik Halatlar

Rope Ø / mm	unit mass / kg/100m	min aggregate breaking force [kN] tensile grade / 1570 N/mm2	min aggregate breaking force [kN] tensile grade / 1770 N/mm2	min aggregate breaking force [kN] tensile grade / 1860 N/mm2	min aggregate breaking force [kN] tensile grade / 1960 N/mm2*
22	238	433	488	513	543
24	284	516	582	612	646
26	334	608	685	720	759
28	387	704	793	833	880
30	445	809	912	958	1010
32	505	919	1036	1089	1149
34	600	1077	1214	1275	1343
36	673	1207	1361	1430	1505
38	749	1345	1516	1593	1677
40	830	1490	1680	1765	1858
43	916	1643	1852	1946	2049
44	1005	1803	2033	2136	2249
46	1098	1971	2222	2335	2458
48	1196	2146	2419	2542	2676
50	1298	2328	2625	2758	2904
52	1403	2518	2839	2983	3141
54	1514	2716	3061	3217	3387
56	1628	2920	3292	3460	3642
58	1746	3133	3532	3711	3907
60	1869	3353	3780	3972	4181
62	1995	3580	4036	4241	4485
64	2126	3814	4300	4519	4757
66	2261	4057	4573	4806	5059