



Dan Strong Polypropylene - 8 Strand

Dia. mm	Dia. Inch	Cir. inch	Wt.Per 220 Mtrs. in Kgs.	Wt Per 200 Mtrs. in Kgs.	Wt.Per 220 Mtrs. in Lbs.	Wt.Per 200 Mtrs. in Lbs.	Mtr/kg	Feet/kg	MBL / kgf	MBL / Lbs	MBL / KN
40	1-5/8	5	158	143.64	347.60	316	1.39	4.57	28000	61600	61600
44	1-3/4	5-1/2	193.60	176	425.92	387.20	1.14	3.73	33750	74250	74250
48	1-15/16	6	229	208.18	503.80	458	0.96	3.15	39500	86900	86900
52	2-1/16	6-1/2	270.40	245.82	594.88	540.80	0.81	2.67	45750	100650	100650
56	2-1/4	7	312	283.64	686.40	624	0.71	2.31	52000	114400	114400
60	2-3/8	7-1/2	359	326.36	789.80	718	0.61	2.01	59500	130900	130900
64	2-1/2	8	407	370	895.40	814	0.54	1.77	67550	148610	148610
68	2-15/16	8-1/2	460	418.18	1012	920	0.48	1.57	76000	167200	167200
72	2-7/8	9	515	468.18	1133	1030	0.43	1.40	84500	185900	185900
76	3	9-1/2	574	521.82	1262.80	1148	0.38	1.26	94000	206800	206800
80	3-1/4	10	638	580	1403.60	1276	0.34	1.13	104000	228800	228800
84	3-1/2	10-1/2	703	639.09	1546.60	1406	0.31	1.03	114000	250800	250800
88	3-15/16	11	772	701.82	1698.40	1544	0.28	0.93	125000	275000	275000
92	3-7/8	11-1/2	846	769.09	1861.20	1692	0.26	0.85	136000	299200	299200
96	3-3/4	12	916	832.73	2015.20	1832	0.24	0.79	148000	325600	325600
100	4	12-1/2	1000	909.09	2200	2000	0.22	0.72	159166	350165.2	350165.2
104	4-1/2	13	1078	980	2371	2155.45	0.20	0.67	169500	372900	372900
112	1-7/8	14	-	1026.40	-	2258	0.17	0.55	195600	430320	430320
116	4-3/4	14-1/2	-	1008.60	-	2218	0.16	0.52	207030	455466	455466
120	5	15	-	1047	-	2303	0.15	0.49	224600	494120	494120