



## Dan Strong Polypropylene - 12 Strand

Dia. mm	Dia. Inch	Cir. inch	Wt.Per 220 Mtrs. in Kgs.	Wt Per 200 Mtrs. in Kgs.	Wt.Per 220 Mtrs. in Lbs.	Wt.Per 200 Mtrs. in Lbs.	Mtr/kg	Feet/kg	MBL / kgf	MBL / Lbs	MBL / KN
52	2-1/16	6-1/2	274	249.09	602.80	548	0.80	2.63	47400	104280	104280
56	2-1/4	7	316	287.27	695.20	632	0.70	2.28	55100	121220	121220
60	2-3/8	7-1/2	364	330.91	800.80	728	0.60	1.98	61700	135740	135740
64	2-1/2	8	413	375.45	908.60	826	0.53	1.75	70500	155100	155100
68	2-15/16	8-1/2	470	427.27	1034	940	0.47	1.54	79800	175560	175560
72	2-7/8	9	523	475.45	1150.60	1046	0.42	1.38	89200	196240	196240
76	3	9-1/2	586	532.73	1289.20	1172	0.38	1.23	98500	216700	216700
80	3-5/32	10	648	589.09	1425.60	1296	0.34	1.11	108400	238480	238480
84	3-1/2	10-1/2	716	650.91	1575.20	1432	0.31	1.01	117800	259160	259160
88	3-7/16	11	787	715.45	1731.40	1574	0.28	0.92	127700	280940	280940
96	3-13/16	12	934	849.09	2054.80	1868	0.24	0.77	150800	331760	331760
104	4-1/2	13	1095	995.45	2409	2190	0.20	0.66	171700	377740	377740
108	4-15/16	13-1/2	1166	1060	2565.2	2332	0.19	0.62	186000	409200	409200
112	1-7/8	14	-	1124.5	-	2474	0.17	0.56	200200	440440	440440
120	5	15	-	1200	-	2640	0.15	0.49	231600	509520	509520